

Sortentabelle DIN 55468-1, Ausgabe 2015

	Sorte	Berstfestigkeit	Durchstoßarbeit <sup>a</sup>	Kantenstauchwiderstand
		kPa	J	kN/m
einwellig	1.01	-	2,5	3,5
	1.02	-	3,0	4,0
	1.03	-	3,5	4,5
	1.04	-	4,0	5,5
	1.05	-	4,5	6,5
	1.10	540	2,5	3,5
	1.20	770	3,0	4,0
	1.30	1000	3,5	4,5
	1.40	1200	4,0	5,5
	1.50	1450	4,5	6,5
mehrwellig	2.02	-	5,5	6,5
	2.03	-	6,0	7,0
	2.04	-	6,5	7,5
	2.05	-	7,0	8,5
	2.06	-	7,5	9,0
	2.20	770	5,5	6,5
	2.30	1000	6,0	7,0
	2.40	1200	6,5	8,0
	2.50	1450	7,5	8,5
	2.60	1650	8,5	9,0
	2.70	2000	9,5	9,5
	2.80	-	11,0	12,0
	2.90	-	13,0	14,0
	2.91	-	16,0	16,0
	2.92	-	21,0	18,0
	2.95	-	24,0	21,0
	2.96	-	27,0	24,0
	ANMERKUNG: Festigkeitswerte gelten nicht für Wellpappen nur aus Wellen D, E, F und G			
<sup>a</sup> Für einwellige Wellpappe in Wellenart B reduzieren sich die angegebenen Werte der Sorten um 10 %				